

5. (Amended) The wiping cloth made of nonwoven fabric according to claim 1, wherein the fibers A and the fibers B are substantially entangled three-dimensionally with each other.

6. The wiping cloth made of nonwoven fabric according to claim 1, wherein the fibers A and the fibers B are continuous fibers.

9. The method for manufacturing a wiping cloth made of nonwoven fabric according to claim 7, wherein a component containing 1.5 to 15 mass percent polyoxyalkyleneglycol of 2000 to 20000 in mass average molecular weight is used as the polyester polymer component A.

10. The method for manufacturing a wiping cloth made of nonwoven fabric according to claim 8, wherein the splitting is carried out by buckling treatment.

11. The method for manufacturing a wiping cloth made of nonwoven fabric according to claim 7, wherein water needling or needle punching carries out the splitting.

12. The method for manufacturing a wiping cloth made of nonwoven fabric according to claim 7, wherein the splittable conjugate fibers are splittable conjugate continuous fibers.

13. The method for manufacturing a wiping cloth made of nonwoven fabric according to claim 7, wherein low-temperature plasma treatment is applied using argon as the inert gas.